

# RIGID FILM / FOIL



RIGID FILM/FOIL								
GRADE	RECOMMENDED USE	TYPICAL PROPERTIES						
		R.D.	SOFTENING POINT	IMPACT STRENGTH KJ/m <sup>2</sup>	SHORE D	TENSILE STRENGTH (Mpa)	ELONGATION	STABILISER
RF500	Clear Film	1.36	75	170	85	45	38	Sn
RF502	Shrink Film	1.30	72	150	81	46	15	Sn
RF503	Foil for Thermoforming	1.36	76	180	83	50	30	Sn
RF504	Film - Stationery Inserts	1.46	79	300	84	63	10	Pb
RF505	Film - Twist Wrap	1.36	76	170	81	45	15	Sn

*Elco Plastics (Pty) Ltd does not make any warranties in regard to the accuracy of the information contained herein. Elco Plastics (Pty) Ltd specifically excludes any liability of any nature or damage that any party may suffer by reason of relying on the information herein.*